



TUFF-PRODUCTS

1902 N 69th St. • Tampa, FL 33619

Office: 813-960-1122 • Toll Free: 800-780-3262 • Email: sales@tuf-link.com

TUF-LINK: DIRECTIONS FOR USE ON POOLS AND DECKS

STAGE 1: PREPARE SURFACES:

- A. All surfaces should be free of dirt, dust, oil, grease, efflorescence, coatings, sealers, and other foreign matter.
- B. Etch surface with a dilute solution of muriatic acid.
- C. Flush with a dilute solution of trisodium phosphate, bicarb, or ammonia to neutralize Step B.
- D. Rinse surface with a dilute solution of bleach to kill fungus and mold spores, and allow to sun dry.

STAGE 2: PRIME-COAT SURFACE WITH DILUTED TUF-LINK:

Brush, roll, or spray a 1-to-1 dilution of TUF-LINK and water. This seals in any salts that may migrate from beneath the surface.

STAGE 3: BOND-COAT SURFACE WITH TUF-LINK:

Apply TUF-LINK full strength for bonding and additional seal.

STAGE 4: FOR USE AS AN ADMIXTURE TO POOL AND DECK MIXES:

- A. Combine first part water* with cement and aggregate mixture. Mix until tight.
- B. Add second part water. Mix until tight.
- C. Add TUF-LINK** to third part water, then introduce to mix. Continue to mix no more than 3-5 minutes.

USAGE:

***NOTE:** When using calcium chloride, always be sure to pre-ad to first part of water and fully dissolve before adding cement and aggregate. Do not add more calcium chloride during mix. Do not overuse.

** 1 quart (32 oz.) of TUF-LINK per 94 lb. bag of cement
12-16 oz. Of TUF-LINK per 80 lb. bag of pre-packaged pool mix. Always post-ad in last part of water.

"Waterborne Chemistry"

WATER RESISTANT CONCRETE BONDING ADHESIVE AND ADMIXTURE